



GENERAL PRODUCT SPECIFICATION

Item No.	UN100-E
-----------------	----------------

Date	03-31-08	Replaces	06-06-06	No. Pages	1
-------------	----------	-----------------	----------	------------------	---

Product Description:

Style	Pads; perforated on centerline for dividing in half for smaller applications.
Item Size (each)	41 cm x 51 cm
Color	Green
Composition	Polypropylene >98%, Surfactant < 1.0%, color pigment < 0.1 %
Structure	96% natural white meltblown nonwoven fibers(<10 microns) 4% white spunbond nonwoven coverstock(<15-30 microns)
Technology	Meltblown + spunbond
Absorbency	Universal (Hydrophilic + Oleophilic)
Bonding	Bonded (staggered pattern) + Mechanical entanglement

Intended Application	Chemical & Static Resistant Sorbent for Water, Oil, or Solvent Base Liquids
-----------------------------	---

Absorbency Capacity	88 l per bale (saturated; medium viscosity-12.5x)
----------------------------	---

Packaging Description:

Package configuration	1-Case	Pkg. Weight	7.1 kg (6.1 kg)
Items per Package	1-Bale / Case	Pkg. Dimensions	53cm x 43cm x 44cm H
Container type	Carton		

Physical Properties:

Parameter	SPC Test Method	Units	Nominal	(+/-)Tolerance
Basis Weight	SPCTM-002	G/M2	295	30
Caliper	SPCTM-020	mm	4.5	0.5
Absorbency** (med visc)	SPCTM-004B	gL/gS	12.5	2
Tensile Strength	SPCTM-007	daN	14	1.4
Color	Visual	-----	Green	per standard

The above properties are “nominal” values used for **PROCESS CONTROL** when the product is produced and/or inspected. Performance “nominals” may vary depending upon the specific application, and/or the environment being applied, stored, or shipped.

**** The "Absorbency" Spec and "SPCTM004" test method is based on the protocol of ASTM F726, using SAE20 non-detergent as the Oil Type, medium viscosity.**

Attributes	Product will be free of foreign material contamination, rips, holes, and tears.
Labeling	Each package to be clearly labeled with Company Name, Address, Item No., Date, and/or Package Code (Bar Code).
Certification	Make no changes in basic process or composition without notifying customer. Claims for non-conformance of goods must be made within 60-days of delivery.

SPC International, Atealaan 71, I.Z. Klein Gent, B-2200 Herentals,Belgium
Tel +32(0)14 321855 Fax +32(0)14 320440