

X5R Dielectric

General Specifications



GENERAL DESCRIPTION

- General Purpose Dielectric for Ceramic Capacitors
- EIA Class II Dielectric
- Temperature variation of capacitance is within $\pm 15\%$ from -55°C to $+85^{\circ}\text{C}$
- Well suited for decoupling and filtering applications
- Available in High Capacitance values (up to $100\mu\text{F}$)

PART NUMBER (see page 2 for complete part number explanation)

1210

Size
(L" x W")
0101**
0201
0402
0603
0805
1206
1210
1812

4

Voltage
4 = 4V
6 = 6.3V
Z = 10V
Y = 16V
3 = 25V
D = 35V
5 = 50V
1 = 100V

D

Dielectric
D = X5R

107

Capacitance Code (In pF)
2 Sig. Digits + Number of Zeros

M

Capacitance Tolerance
K = $\pm 10\%$
M = $\pm 20\%$

A

Failure Rate
A = N/A

T

Terminations
T = Plated Ni and Sn

2

Packaging
2 = 7" Reel
4 = 13" Reel
7 = Bulk Cass.
9 = Bulk
U = 4mm TR (01005)

A



Special Code
A = Std.



**EIA 01005

NOTE: Contact factory for availability of Tolerance Options for Specific Part Numbers.
Contact factory for non-specified capacitance values.

TYPICAL ELECTRICAL CHARACTERISTICS



Specifications and Test Methods

Parameter/Test		X5R Specification Limits	Measuring Conditions	
Operating Temperature Range		-55°C to +85°C	Temperature Cycle Chamber	
Capacitance		Within specified tolerance	Freq.: 1.0 kHz $\pm$ 10% Voltage: 1.0Vrms $\pm$.2V For Cap > 10 μ F, 0.5Vrms @ 120Hz	
Dissipation Factor		$\leq$ 2.5% for $\geq$ 50V DC rating $\leq$ 3.0% for 25V DC rating $\leq$ 12.5% Max. for 16V DC rating and lower Contact Factory for DF by PN		
Insulation Resistance		10,000M Ω or 500M Ω - μ F, whichever is less		
Dielectric Strength		No breakdown or visual defects	Charge device with rated voltage for 120 $\pm$ 5 secs @ room temp/humidity Charge device with 300% of rated voltage for 1-5 seconds, w/charge and discharge current limited to 50 mA (max)	
Resistance to Flexure Stresses	Appearance	No defects	Deflection: 2mm Test Time: 30 seconds  1mm/sec 90 mm	
	Capacitance Variation	$\leq \pm 12\%$		
	Dissipation Factor	Meets Initial Values (As Above)		
	Insulation Resistance	$\geq$ Initial Value x 0.3		
Solderability		$\geq$ 95% of each terminal should be covered with fresh solder	Dip device in eutectic solder at 230 $\pm$ 5°C for 5.0 $\pm$ 0.5 seconds	
Resistance to Solder Heat	Appearance	No defects, <25% leaching of either end terminal	Dip device in eutectic solder at 260°C for 60 seconds. Store at room temperature for 24 $\pm$ 2 hours before measuring electrical properties.	
	Capacitance Variation	$\leq \pm 7.5\%$		
	Dissipation Factor	Meets Initial Values (As Above)		
	Insulation Resistance	Meets Initial Values (As Above)		
	Dielectric Strength	Meets Initial Values (As Above)		
Thermal Shock	Appearance	No visual defects	Step 1: -55°C $\pm$ 2°	30 $\pm$ 3 minutes
	Capacitance Variation	$\leq \pm 7.5\%$	Step 2: Room Temp	$\leq$ 3 minutes
	Dissipation Factor	Meets Initial Values (As Above)	Step 3: +85°C $\pm$ 2°	30 $\pm$ 3 minutes
	Insulation Resistance	Meets Initial Values (As Above)	Step 4: Room Temp	$\leq$ 3 minutes
	Dielectric Strength	Meets Initial Values (As Above)	Repeat for 5 cycles and measure after 24 $\pm$ 2 hours at room temperature	
Load Life	Appearance	No visual defects	Charge device with 1.5X rated voltage in test chamber set at 85°C $\pm$ 2°C for 1000 hours (+48, -0). Note: Contact factory for *optional specification part numbers that are tested at < 1.5X rated voltage. Remove from test chamber and stabilize at room temperature for 24 $\pm$ 2 hours before measuring.	
	Capacitance Variation	$\leq \pm 12.5\%$		
	Dissipation Factor	$\leq$ Initial Value x 2.0 (See Above)		
	Insulation Resistance	$\geq$ Initial Value x 0.3 (See Above)		
	Dielectric Strength	Meets Initial Values (As Above)		
Load Humidity	Appearance	No visual defects	Store in a test chamber set at 85°C $\pm$ 2°C/ 85% $\pm$ 5% relative humidity for 1000 hours (+48, -0) with rated voltage applied. Remove from chamber and stabilize at room temperature and humidity for 24 $\pm$ 2 hours before measuring.	
	Capacitance Variation	$\leq \pm 12.5\%$		
	Dissipation Factor	$\leq$ Initial Value x 2.0 (See Above)		
	Insulation Resistance	$\geq$ Initial Value x 0.3 (See Above)		
	Dielectric Strength	Meets Initial Values (As Above)		

X5R Dielectric

Capacitance Range



PREFERRED SIZES ARE SHADED

Case Size		0101*		0201			0402					0603					0805													
Soldering		Reflow Only		Reflow Only			Reflow/Wave					Reflow/Wave					Reflow/Wave													
Packaging		Paper/Embossed		All Paper			All Paper					All Paper					Paper/Embossed													
(L) Length	mm (in.)	0.40 ± 0.02 (0.016 ± 0.0008)		0.60 ± 0.03 (0.024 ± 0.001)			1.00 ± 0.10 (0.040 ± 0.004)					1.60 ± 0.15 (0.063 ± 0.006)					2.01 ± 0.20 (0.079 ± 0.008)													
(W) Width	mm (in.)	0.20 ± 0.02 (0.008 ± 0.0008)		0.30 ± 0.03 (0.011 ± 0.001)			0.50 ± 0.10 (0.020 ± 0.004)					0.81 ± 0.15 (0.032 ± 0.006)					1.25 ± 0.20 (0.049 ± 0.008)													
(t) Terminal	mm (in.)	0.10 ± 0.04 (0.004 ± 0.016)		0.15 ± 0.05 (0.006 ± 0.002)			0.25 ± 0.15 (0.010 ± 0.006)					0.35 ± 0.15 (0.014 ± 0.006)					0.50 ± 0.25 (0.020 ± 0.010)													
Voltage:		6.3	10	4	6.3	10	16	25	4	6.3	10	16	25	50	4	6.3	10	16	25	35	50	4	6.3	10	16	25	35	50		
Cap (pF)	100 101		B					A																						
	150 151		B					A																						
	220 221		B					A					C																	
	330 331		B					A					C																	
	470 471		B					A					C																	
	680 681		B					A					C																	
	1000 102		B				A	A					C																	
	1500 152	B	B				A	A					C																	
	2200 222	B	B			A	A	A					C																	
	3300 332	B	B			A	A	A					C																	
	4700 472	B	B			A	A	A				C							G											
	6800 682	B	B			A	A	A				C							G											
Cap (µF)	0.01 103	B	B			A	A	A				C					G	G	G											
	0.015 153	B										C					G	G	G											
	0.022 223	B			A						C	C					G	G	G								N			
	0.033 333	B									C						G	G	G									N		
	0.047 473	B			A						C	C					G	G	G									N		
	0.068 683	B									C						G		G									N		
	0.1 104	B			A	A				C	C	C	C				G	G	G							N	N	N		
	0.15 154																G									N	N			
	0.22 224	B			A	A	A			C	C	C					G	G								N	N	N		
	0.33 334																G	G								N				
	0.47 474				A	A				C	C	C	C				G	J								N	P	P		
	0.68 684																G									N				
	1.0 105				A	A				C	C	C	C			G	G	G	G	J	G	G				N	N	P	P	
	1.5 155																													
	2.2 225				A	A				C	C	C				G	G	J	J	J						N	N	N	P	P
	3.3 335															J	J	J	J							N	N			
	4.7 475									E	E					J	J	J	G						N	N	N	N	P	P
	10 106									E	E					K	J	J							N	N	N	N	P	
	22 226															K	K								N	N	P	P		
	47 476																								P	P				
	100 107																								P					
Voltage:		6.3	10	4	6.3	10	16	25	4	6.3	10	16	25	50	4	6.3	10	16	25	35	50	4	6.3	10	16	25	35	50		
Case Size		0101*		0201			0402					0603					0805													

Letter	A	B	C	E	G	J	K	M	N	P	Q	X	Y	Z
Max. Thickness	0.33 (0.013)	0.22 (0.009)	0.56 (0.022)	0.71 (0.028)	0.90 (0.035)	0.94 (0.037)	1.02 (0.040)	1.27 (0.050)	1.40 (0.055)	1.52 (0.060)	1.78 (0.070)	2.29 (0.090)	2.54 (0.100)	2.79 (0.110)
PAPER						EMBOSS								

NOTE: Contact factory for non-specified capacitance values

*EIA 01005



X5R Dielectric

Capacitance Range



PREFERRED SIZES ARE SHADED

Case Size		1206								1210								1812							
Soldering		Reflow/Wave								Reflow Only								Reflow Only							
Packaging		Paper/Embossed								Paper/Embossed								All Embossed							
(L) Length	mm	3.20 ± 0.20								3.20 ± 0.20								4.50 ± 0.30							
	(in.)	(0.126 ± 0.008)								(0.126 ± 0.008)								(0.177 ± 0.012)							
(W) Width	mm	1.60 ± 0.20								2.50 ± 0.20								3.20 ± 0.20							
	(in.)	(0.063 ± 0.008)								(0.098 ± 0.008)								(0.126 ± 0.008)							
(T) Terminal	mm	0.50 ± 0.25								0.50 ± 0.25								0.61 ± 0.36							
	(in.)	(0.020 ± 0.010)								(0.020 ± 0.010)								(0.024 ± 0.014)							
Voltage:		4	6.3	10	16	25	35	50	100	4	6.3	10	16	25	35	50		4	6.3	10	16	25	35	50	
Cap (pF)	100	101																							
	150	151																							
	220	221																							
	330	331																							
	470	471																							
	680	681																							
	1000	102																							
	1500	152																							
	2200	222																							
	3300	332																							
	4700	472																							
	6800	682																							
Cap (µF)	0.01	103																							
	0.015	153																							
	0.022	223																							
	0.033	333																							
	0.047	473																							
	0.068	683																							
	0.1	104																							
	0.15	154																							
	0.22	224																							
	0.33	334																							
	0.47	474					Q	Q							X	X									
	0.68	684																							
	1.0	105					Q	Q	Q	Q				X	X	X									
	1.5	155																							
	2.2	225				Q	Q	Q	Q	Q	Q			X	Z	Z									
	3.3	335				Q	Q																		
	4.7	475	Q	Q	Q	Q	Q	Q	Q	X			Q	Q	Z	Z	Z								
	10	106	Q	Q	Q	Q	Q	Q	Q	X			X	X	Z	Z	Z						Z		
	22	226	Q	Q	Q	Q	Q						Z	Z	Z	Z	Z								
	47	476	Q	Q	Q								Z	Z	Z	Z				Z					
	100	107	Q	Q									Z	Z	Z	Z									
Voltage		4	6.3	10	16	25	35	50	100	4	6.3	10	16	25	35	50		4	6.3	10	16	25	35	50	
Case Size		1206								1210								1812							

Letter	A	B	C	E	G	J	K	M	N	P	Q	X	Y	Z
Max. Thickness	0.33 (0.013)	0.22 (0.009)	0.56 (0.022)	0.71 (0.028)	0.90 (0.035)	0.94 (0.037)	1.02 (0.040)	1.27 (0.050)	1.40 (0.055)	1.52 (0.060)	1.78 (0.070)	2.29 (0.090)	2.54 (0.100)	2.79 (0.110)
PAPER							EMBOSS							

NOTE: Contact factory for non-specified capacitance values

*EIA 01005

