# CX3399760 | 1250110 EMPTY DUCT COEX

## ConQuest® Empty Conduit, 1 1/4 in, SDR 11, orange



### **Product Classification**

Product TypeEmpty conduitProduct BrandConQuest®

## General Specifications

**Color** Orange

Conduit TypeNon-toneableDensity Test MethodASTM D792A

 Density, maximum
  $0.955 \text{ g/cm}^3$  |  $0.035 \text{ lb/in}^3$  

 Density, minimum
  $0.941 \text{ g/cm}^3$  |  $0.034 \text{ lb/in}^3$ 

**Design Standard** ASTM D3350-05

Wall Type Smooth

#### Dimensions

**Length** 914.4 m | 3000 ft

Inner Diameter, nominal33.985 mm1.338 inOuter Diameter, nominal42.164 mm1.66 in

Wall Thickness Designation SDR 11

Wall Thickness, minimum 3.835 mm | 0.151 in

Nominal Size 1-1/4 in

## Material Specifications

Flexural Modulus, minimum 551.581 N/mm<sup>2</sup> | 80000 psi

Flexural Property Test Method ASTM D790

**Hydrostatic Design Basis**Not pressure rated

Hydrostatic Design Test Method ASTM D2837

COMMSCOPE®

# CX3399760 | 1250110 EMPTY DUCT COEX

Material Type High density polyethylene (HDPE)

Melt Flow Rate Test MethodASTM D1238Melt Flow Rate, maximum0.39 g/10 min

Mechanical Specifications

Minimum Bend Radius, unsupported 457.2 mm | 18 in

**Tensile Property Test Method** ASTM D638

**Tensile Strength at yield, minimum** 20.684 N/mm<sup>2</sup> | 3000 psi

**Pulling Tension, maximum** 689.46 kg | 1520 lb

**Environmental Specifications** 

**Environmental Stress Crack Resistance** Failure rate of 10% within 96 hours **Environmental Stress Test Method** ASTM D1693, ESCR Condition B

Packaging and Weights

**Weight, net** 476.212 kg/km | 320 lb/kft

Regulatory Compliance/Certifications

Agency Classification

ISO 9001:2015 Designed, manufactured and/or distributed under this quality management system



### \* Footnotes

Environmental Stress Crack Resistance ESCR—e Environmental Stress Crack Resistence

