




Meets ANSI/ESD S20.20 and Packaging standard ANSI/ESD S541



* Lids sold separately

Features

- Shields ESD sensitive items from electrostatic charges and electrostatic discharges (with lid in place).
- Available with optional lid, steel reinforcing frame for additional strength and durability, ESD handles, and permanently static dissipative bottom foam pad for cushioning
- Impregnated corrugated material; greater durability than coated or printed material
- Constructed with double sides, double (boxes under 6" deep) or triple (boxes over 6" deep) ends, and single (boxes under 6" deep) or double (boxes over 6" deep) thickness bottom for greater durability
- Surface Resistance: 1×10^6 to $< 1 \times 10^9$ ohms per ANSI/ESD STM11.11 - minimizing the potential of rapid discharge or sparking
- Buried shielding layer minimizing the potential of sloughing and rub-off contamination
- Made from 100% recycled material, and is 100% recyclable
- No tooling cost
- Easy assembly without the need for tape, glue, or staples
- Reusable, ensuring low cost

SPECIFICATIONS

Properties

Surface Resistance

Discharge Shielding

Sloughing Test

Recyclability

Typical Values

1×10^6 to $< 1 \times 10^9$ ohms

< 50 nanoJoules

Negligible surface damage at 10 cycles and $< 5\%$ of surface damage at 200 cycles in Taber Abrasion Test.

No conductive particles abraded from surface

Complete recyclability of package

Test Procedures/Method

ANSI/ESD STM11.11

ANSI/ESD STM11.31

ASTM D4060 at 70 rpm with CS-17 abrasive-coated wheels and 1000 grams load

Rockwell International Test Report of January 8, 1992

Rockwell International Test Report of January 8, 1992



Made in the
United States of America

STORAGE CONTAINERS

PROTEKTIVE PAK
BURIED SHIELDING LAYER

PROTEKTIVE PAK
13520 MONTE VISTA AVENUE, CHINO, CA 91710
PHONE (909) 627-2578
ProtektivePak.com

DRAWING NUMBER
37500

DATE:
February
2015