

AS2502 2-Part Fast Curing Adhesive Sealant

Introduction

AS2502 is a novel accelerated condensation curing package, which consists of an acetoxysilane (A part) sealant and an accelerator (B part) in a 10 : 1 volumetric ratio. By extruding the system through a static mixer nozzle, the intimately mixed system behaves like a conventional silicone sealant, but has the advantage of very rapid cure - less than 1 hour to almost full cure and sufficient cure to enable handling after 25 minutes.

Key Features

- Good adhesion and fast assembly
- Heat accelerated cure at 120°C
- sufficient anaerobic cure for handling in 25 minutes (not possible with conventional 1-Part RTV sealants)
- similar physical properties to the conventional sealant
- can be heat accelerated

Use and Cure Information

How to Use

AS2502 is supplied as two components, AS2502A sealant and AS2502B accelerator packaged in a 10 to 1 ratio twin cartridge. AS2502 is also suitable for machine dispensing. The dispensing machine must be set to deliver 10 parts of A and 1 part of B by VOLUME, through a static mixing nozzle and then applied to the application. IMPORTANT the mixed components will cure in the nozzle so to preserve nozzles a continuous process is required or a change of nozzle after the task is completed. A nozzle of at least 20 folds is recommended for uniform mixing of both components. Dispensing by weight requires 10 parts of A and 1.17 parts of B.

Automated dispensing machinery is available through ACC Silicones, please discuss with your Regional Sales Manager.

Application and Cure

Ensure the surface is clean and dry (recommend using ACC Degreaser) before applying the AS2502 package. Complete mixing of each component is achieved within the first 50-60% of the nozzle. The extruded sealant should be applied to the substrate immediately and tooled within 1 minute of application.

Heat acceleration at 120°C will give a full cure within 1 hour.

Temperature Resistance

Laboratory tests at 250°C, over a 196 hour period and 300°C over a 72 hour period have showed AS2502 to remain flexible and retain its adhesive properties.

Low temperature testing at -65°C for a 10 minute period gave a hardening of the product but no cracking or failure of adhesion was observed (laboratory tests performed by preparing a cured sample on an aluminium test panel and carbon dioxide solid /dry ice was used to crash cool the sample).

Revision date: 14/04/2011

The information and recommendations in this publication are to the best of our knowledge reliable. However nothing herein is to be construed as a warranty or representation. Users should make their own tests to determine the applicability of such information or the suitability of any products for their own particular purposes. Statements concerning the use of the products described herein are not to be construed as recommending the infringement of any patent and no liability for infringement arising out of any such use is to be assumed.

ACC Silicones Ltd, Amber House,
Showground Road, Bridgwater, Somerset, UK
Tel. +44(0)1278 411400 Fax. +44(0)1278 411444

Property

Uncured Products

Colour:	A Part	Red
	B Part	Black
Appearance:	A Part	Paste
	B Part	Paste
SG:	A Part	1.03
	B Part	1.20
Viscosity mPa.s:	A Part	72000
	B Part	300000
Tack Free Time:		4 minutes *
Cure Through:		<1hour *
* measured at 23+/-2°C and 65% relative humidity.		

Cured Elastomer

(after 7 days cure at 23+/-2°C and 65% relative humidity)

Tensile Strength:	BS903 Part A2	1.50 MPa
Elongation at Break:	BS903 Part A2	260 %
Youngs Modulus:		0.38 MPa
Modulus at 100% Strain:	BS903 Part A2	0.50 MPa
Tear Strength:	BS903 Part A3	4.00k N/m
Hardness:	ASTM D 2240-95	30 Shore A
Specific Gravity:	BS 903 Part A1	1.06
Linear Shrinkage:		<1.0%
Thermal Conductivity:		0.20 W/mK
Coefficient of Thermal Expansion:		
Volumetric		876 ppm / °C
Linear		292 ppm / °C
Min. Service Temperature:		-65 °C
Max. Service Temperature:	AFS 1540B	+250 °C

Electrical Properties

Volume Resistivity:	ASTM D-257	2.10E+14Ω.cm
Surface Resistivity:	ASTM D-257	1.24E+16Ω
Dielectric Strength:	ASTM D-149	>18 kV/mm
Dielectric Constant at 1MHz:	ASTM D-150	3.0
Dissipation Factor at 1MHz:	ASTM D-150	2.6E-3

Adhesion Testing

Good adhesion to many substrates including glass stainless steel, aluminium and most plastics.

Customers are advised to carry out their own tests on clean, degreased substrates to ensure satisfactory adhesion is achieved. All values are typical and should not be accepted as a specification.

Health and Safety - Material Safety Data Sheets available on request.

Packages – 264 ml 10 to 1 twin cartridges, Please discuss with your regional sales manager for alternative packing options for machinery dispensing.

Storage and Shelf Life – Expected to be 12 months in original, unopened containers below 40°C.

Treco S.R.L., Via Romagna N.8,
20098 Sesto Ulteriano (MI), Italia.
Tel. 39/02/9880913 Fax. +39/02/98280413