

# Soldering Tips



## Coating Standard for Soldering Tips :

Alloy Iron Coating Thickness : 0.3µm

Nickel Coating Thickness : 0.2µm


Chrome Coating Thickness : 0.2µm

Alloy Iron coated iron tips perform excellent on temperature during 360°C and 380°C

It can only work 4-5 hours if tips continuous get heat up beyond 450°C

Chrome layer will lose effect if temperature is up to 500°C

Dimension Tolerance is +0.02mm




Tip out diameter Ø6.5




# Soldering Tips




-10°C to -18°F  
21-10150



-10°C to -18°F  
21-10152




0°C  
21-10154



0°C  
21-10156



0°C  
21-10158



All tips sold separately

## Part Number Table

Description	Part Number
Tip, Chisel, 0.8mm	21-10140
Tip, Chisel, 1.2mm	21-10142
Tip, Chisel, 1.6mm	21-10144
Tip, Chisel, 2.4mm	21-10146
Tip, Conical, 0.5mm	21-10148
Tip, Conical, 0.2mm	21-10150
Tip, Chisel, Angled, 2mm	21-10152
Tip, Chisel, Angled, 3mm	21-10154
Tip, Chisel, Angled, 4mm	21-10156
Tip, Conical, Micro, 0.2mm	21-10158

**Important Notice :** This data sheet and its contents (the "Information") belong to the members of the Premier Farnell group of companies (the "Group") or are licensed to it. No licence is granted for the use of it other than for information purposes in connection with the products to which it relates. No licence of any intellectual property rights is granted. The Information is subject to change without notice and replaces all data sheets previously supplied. The Information supplied is believed to be accurate but the Group assumes no responsibility for its accuracy or completeness, any error in or omission from it or for any use made of it. Users of this data sheet should check for themselves the Information and the suitability of the products for their purpose and not make any assumptions based on information included or omitted. Liability for loss or damage resulting from any reliance on the Information or use of it (including liability resulting from negligence or where the Group was aware of the possibility of such loss or damage arising) is excluded. This will not operate to limit or restrict the Group's liability for death or personal injury resulting from its negligence. Tenma is the registered trademark of the Group. © Premier Farnell plc 2012.

