


# **DATA SHEET**

### Product Number: 110-13-320-41-801100



## **Description:**

DIP Socket
Integral Decoupling Capacitor
Standard Solder Tail (RoHS
Compliant)
Open Frame
Through Hole
Accepts .015-.025" Leads
Plating Code:

13

**Shell Plating:** 

10  $\mu$ " Gold over 100  $\mu$ " Nickel Inner Contact Plating:

30  $\mu^{\text{\tiny{II}}}$  Gold over 50  $\mu^{\text{\tiny{II}}}$  Nickel

Packaging:

Packaged in Tubes

# Of Pins	A	В	С	Qty. per Tube	Mill-Max Part Number	RoHS Compliant
20	1.000	0.300	0.400	20	110-13-320-41-801100	RoHS 2002/95/EC

## **CONTACT:**

Contact Used: #30, Standard 4 Finger Contact

Current Rating = 3 Amps


**BERYLLIUM COPPER ALLOY** 172 (UNS C17200) per ASTM B 194

## **Properties of BERYLLIUM COPPER:**

- Chemical composition: Cu 98.1%, Be 1.9%
- Temper as stamped: TD01

Properties after heat treatment (TH01):

- Hardness: 36-43 Rockwell C
- Mechanical Life: 100 Cycles Min.
- Density: .298 lbs/in3
- Electrical Conductivity: 22% IACS\*
- Resistance: 10 miliohms Max
- Operating Temperature: -55°C/+125°C
- Melting point: 980°C/865°C (liquidus/solidus)
- Stress Relaxation†: 96% of stress remains after 1,000 hours @ 100  $^{\circ}$ C; 70% of stress remains after 1,000 hours @ 200  $^{\circ}$ C



†Since BeCu loses its spring properties over time at high temperatures; it is rated for continuous use up to 150°C. For applications up to 300°C, Mill-Max offers many contacts in Beryllium Nickel. Contact Tech Support for more info.

<sup>\*</sup>International Annealed Copper Standard, i.e. as a % of pure copper.

#### LOOSE PIN:

Loose Pin Used: 1001

BRASS ALLOY (UNS C36000) per ASTM B 16

## **Properties of BRASS ALLOY:**

• Chemical composition: Cu 61.5%, Zn 35.4%, Pb 3.1%†

• Hardness as machined: 80-90 Rockwell B

• Density: .307 lbs/in3

• Electrical conductivity: 26% IACS\*

• Melting point: 900°C/885°C (liquidus/solidus)

†(3 to 4% lead is used to permit "free machining" and is permitted by EC Directive 2002/95Annex 6; so all pin materials are RoHS compliant)

\*International Annealed Copper Standard, i.e. as a % of pure copper.

### **INSULATOR INFORMATION:**

PCT Polyester, (Thermx CG933, black)

High Temperature

### **Properties of PCT Polyester:**

Brand: ThermxGrade: CG-933

Rated voltage: 100 VRMS/150 VDC

• Insulation resistance: 10,000 Megaohms min.

• Material Heat Deflection Temp (per ASTM D 648): 529°F (276°C) @ 66 psi

• Dielectric strength: 1000 VRMS min. (700 VRMS min. for series 117 Shrink DIP)

Note: Materials above 446°F (230°C) are considered suitable for "eutectic" reflow soldering, above 500°F (260°C) for "lead-free" reflow soldering.