Distributed by:

JAMECO® ELECTRONICS

www.Jameco.com ✦ 1-800-831-4242

The content and copyrights of the attached material are the property of its owner.

Jameco Part Number 1059709

X5R Dielectric

General Specifications



GENERAL DESCRIPTION

- General Purpose Dielectric for Ceramic Capacitors
- EIA Class II Dielectric
- Temperature variation of capacitance is within ±15% from -55°C to +85°C
- Well suited for decoupling and filtering applications
- Available in High Capacitance values (up to 100µF)

PART NUMBER (see page 2 for complete part number explanation)

1210	4	D	107	M	A	T	2	A
Size (L" x W")	**Voltage** 4 = 4V, 6 = 6.3V, Z = 10V, Y = 16V, 3 = 25V, D = 35V, 5 = 50V	**Dielectric** D = X5R	**Capacitance Code (In pF)** 2 Sig. Digits + Number of Zeros	**Capacitance Tolerance** K = ±10%, M = ±20%	**Failure Rate** A = N/A	**Terminations** T = Plated Ni and Sn	**Packaging** 2 = 7" Reel, 4 = 13" Reel, 7 = Bulk Cass., 9 = Bulk	**Special Code** A = Std.

NOTE: Contact factory for availability of Tolerance Options for Specific Part Numbers.
Contact factory for non-specified capacitance values.

TYPICAL ELECTRICAL CHARACTERISTICS





X5R Dielectric

Specifications and Test Methods

Parameter/Test		X5R Specification Limits	Measuring Conditions	
Operating Temperature Range		-55ºC to +85ºC	Temperature Cycle Chamber	
Capacitance		Within specified tolerance	Freq.: 1.0 kHz ± 10% Voltage: 1.0Vrms ± .2V For Cap > 10 µF, 0.5Vrms @ 120Hz	
Dissipation Factor		≤ 2.5% for ≥ 50V DC rating ≤ 3.0% for 25V DC rating ≤ 3.5% for 16V DC rating ≤ 5.0% for ≤ 10V DC rating		
Insulation Resistance		100,000MΩ or 500MΩ - µF, whichever is less	Charge device with rated voltage for 120 ± 5 secs @ room temp/humidity	
Dielectric Strength		No breakdown or visual defects	Charge device with 300% of rated voltage for 1-5 seconds, w/charge and discharge current limited to 50 mA (max)	
Resistance to Flexure Stresses	Appearance	No defects	Deflection: 2mm Test Time: 30 seconds 	
	Capacitance Variation	≤ ±12%		
	Dissipation Factor	Meets Initial Values (As Above)		
	Insulation Resistance	≥ Initial Value x 0.3		
Solderability		≥ 95% of each terminal should be covered with fresh solder	Dip device in eutectic solder at 230 ± 5ºC for 5.0 ± 0.5 seconds	
Resistance to Solder Heat	Appearance	No defects, <25% leaching of either end terminal	Dip device in eutectic solder at 260ºC for 60 seconds. Store at room temperature for 24 ± 2 hours before measuring electrical properties.	
	Capacitance Variation	≤ ±7.5%		
	Dissipation Factor	Meets Initial Values (As Above)		
	Insulation Resistance	Meets Initial Values (As Above)		
	Dielectric Strength	Meets Initial Values (As Above)		
Thermal Shock	Appearance	No visual defects	Step 1: -55ºC ± 2º	30 ± 3 minutes
	Capacitance Variation	≤ ±7.5%	Step 2: Room Temp	≤ 3 minutes
	Dissipation Factor	Meets Initial Values (As Above)	Step 3: +85ºC ± 2º	30 ± 3 minutes
	Insulation Resistance	Meets Initial Values (As Above)	Step 4: Room Temp	≤ 3 minutes
	Dielectric Strength	Meets Initial Values (As Above)	Repeat for 5 cycles and measure after 24 ± 2 hours at room temperature	
Load Life	Appearance	No visual defects	Charge device with 1.5X rated voltage in test chamber set at 85ºC ± 2ºC for 1000 hours (+48, -0). Note: Contact factory for specific high CV devices that are tested at 1.5X rated voltage. Remove from test chamber and stabilize at room temperature for 24 ± 2 hours before measuring.	
	Capacitance Variation	≤ ±12.5%		
	Dissipation Factor	≤ Initial Value x 2.0 (See Above)		
	Insulation Resistance	≥ Initial Value x 0.3 (See Above)		
	Dielectric Strength	Meets Initial Values (As Above)		
Load Humidity	Appearance	No visual defects	Store in a test chamber set at 85ºC ± 2ºC/ 85% ± 5% relative humidity for 1000 hours (+48, -0) with rated voltage applied. Remove from chamber and stabilize at room temperature and humidity for 24 ± 2 hours before measuring.	
	Capacitance Variation	≤ ±12.5%		
	Dissipation Factor	≤ Initial Value x 2.0 (See Above)		
	Insulation Resistance	≥ Initial Value x 0.3 (See Above)		
	Dielectric Strength	Meets Initial Values (As Above)		

X5R Dielectric

Capacitance Range

PREFERRED SIZES ARE SHADED

SIZE		0201				0402						0603							0805						1206						1210							1812			
Soldering		Reflow Only				Reflow Only						Reflow Only							Reflow/Wave						Reflow/Wave						Reflow/Wave							Reflow Only			
Packaging		All Paper				All Paper						All Paper							Paper/Embossed						Paper/Embossed						Paper/Embossed							All Embossed			
(L) Length	MM	0.60 ± 0.03				1.00 ± 0.10						1.60 ± 0.15							2.01 ± 0.20						3.20 ± 0.20						3.20 ± 0.20							4.50 ± 0.30			
	(in.)	(0.024 ± 0.001)				(0.040 ± 0.004)						(0.063 ± 0.006)							(0.079 ± 0.008)						(0.126 ± 0.008)						(0.126 ± 0.008)							(0.177 ± 0.012)			
(W) Width	MM	0.30 ± 0.03				0.50 ± 0.10						0.81 ± 0.15							1.25 ± 0.20						1.60 ± 0.20						2.50 ± 0.20							3.20 ± 0.20			
	(in.)	(0.011 ± 0.001)				(0.020 ± 0.004)						(0.032 ± 0.006)							(0.049 ± 0.008)						(0.063 ± 0.008)						(0.098 ± 0.008)							(0.126 ± 0.008)			
(t) Terminal	MM	0.15 ± 0.05				0.25 ± 0.15						0.35 ± 0.15							0.50 ± 0.25						0.50 ± 0.25						0.50 ± 0.25							0.61 ± 0.36			
	(in.)	(0.006 ± 0.002)				(0.010 ± 0.006)						(0.014 ± 0.006)							(0.020 ± 0.010)						(0.020 ± 0.010)						(0.020 ± 0.010)							(0.024 ± 0.014)			
	WVDC	6.3	10	16	25	4	6.3	10	16	25	50	4	6.3	10	16	25	35	50	6.3	10	16	25	35	50	6.3	10	16	25	35	50	4	6.3	10	16	25	35	50	6.3	10	25	50
Cap (pF)	100				A																																				
	150				A																																				
	220				A						C																														
	330				A						C																														
	470				A						C																														
	680				A						C																														
	1000			A	A						C																														
	1500			A							C																														
	2200		A	A							C																														
	3300		A								C																														
	4700		A							C								G																							
	6800		A							C								G																							
Cap (µF)	0.010		A							C								G																							
	0.015									C						G	G	G																							
	0.022	A							C	C						G	G	G						N																	
	0.033								C							G	G	G						N																	
	0.047	A							C							G	G	G						N																	
	0.068								C							G		G						N																	
	0.10	A						C	C							G		G				N		N																	
	0.15															G						N	N																		
	0.22						C								G	G						N	N							Q											
	0.33														G	G						N																			
	0.47					C	C								G							N						Q	Q								X				
	0.68														G							N																			
	1.0					C	C	C					G	G	G	J					N	N		P*				Q	Q						X	X	X				
	1.5																			N	N																				
	2.2					C						G	G	J	J					N	N	N					Q	Q						Z	X					Z
	3.3																		N	N						Q	Q	Q						Z						
	4.7											G	G						N	N	N	N*				Q	Q	Q					Z	Z							
	10											K							N	N	N				Q	Q	Q	Q				Z									
	22																		N						Q	Q	Q					Z	Z	Z	Z*						
	47																								Q							Z									
	100																														Z	Z*									
	WVDC	6.3	10	16	25	4	6.3	10	16	25	50	4	6.3	10	16	25	35	50	6.3	10	16	25	35	50	6.3	10	16	25	35	50	4	6.3	10	16	25	35	50	6.3	10	25	50
SIZE		0201				0402						0603							0805						1206						1210							1812			



Letter	A	E	G	J	K	M	N	Q	X	Y	Z
Max. Thickness	0.33 (0.013)	0.71 (0.028)	0.86 (0.034)	0.94 (0.037)	1.02 (0.040)	1.27 (0.050)	1.40 (0.055)	1.78 (0.070)	2.29 (0.090)	2.54 (0.100)	2.79 (0.110)
	PAPER				EMBOSSED						

= **Under Development**

*Optional Specifications – Contact factory

NOTE: Contact factory for non-specified capacitance values