



BAG, LOW CHARGING PINK POLY

Transparent light pink, low density polyethylene bags have low charging (antistatic) properties.

Specifications:

Electrical Properties

Static Decay:	< 1.0 sec.
Surface Resistance:	1×10^9 to 1×10^{13} ohms
Polycarbonate Haze:	NE
Corrosivity Observations:	NE

Typical Value

Test Procedures/Method

ASTM 101 Method 4046
ANSI/ESD STM11.11
72 hr contact
MIL-STD-3010, M3005

Physical Properties

Material Thickness:	4.0mils (0.004", 0.1016mm), +/- 10%
Melt Index:	0.050 gm/ 10 min
Density:	0.923 gm/cc
Dart Impact:	230 gms
Coefficient of Friction:	MD 24,000 psi
1% Secant Modulus (Stiffness):	MD 25,000 psi

ASTM D-1283
ASTM D-1505
ASTM D-1709
ASTM D-1894 (unmodified film)
ASTM D-882

Pink Poly bags should be used within a timely manner and should not be reused as the ESD properties will negate over time

RoHS, REACH and Conflict Minerals Statement

See the Desco Industries RoHS, Reach and Conflict Minerals Statement:
Descoindustries.com/ROHS3.aspx

See the Protektive Pak Limited Warranty:
Protektivepak.Descoindustries.com/Limited-Warranty.aspx



Made in the
United States of America

Specifications are subject to change without notice.

Dimensional tolerances unless otherwise specified:
L: +/- 0.250" / W: +/- 0.250"

TRANSPARENT LOW CHARGING (PINK POLY) BAGS

PROTEKTIVE PAK

PROTEKTIVE PAK
13520 MONTE VISTA AVENUE, CHINO, CA 91710
PHONE (909) 627-2578
ProtektivePak.com

DRAWING
NUMBER
49100

DATE
May
2023