

GELOYTM RESIN XP4025

REGION AMERICAS

DESCRIPTION

PC/ASA. Excellent weatherability.

TYPICAL PROPERTY VALUES

Revision 20190925

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
MECHANICAL			
Tensile Stress, yld, Type I, 50 mm/min	59	MPa	ASTM D 638
Tensile Strain, brk, Type I, 50 mm/min	25	%	ASTM D 638
Flexural Stress, yld, 1.3 mm/min, 50 mm span	88	MPa	ASTM D 790
Flexural Modulus, 1.3 mm/min, 50 mm span	2580	MPa	ASTM D 790
Hardness, Rockwell R	114	-	ASTM D 785
Tensile Stress, yield, 50 mm/min	58	MPa	ISO 527
Tensile Stress, break, 50 mm/min	45	MPa	ISO 527
Tensile Strain, yield, 50 mm/min	4.1	%	ISO 527
Tensile Strain, break, 50 mm/min	64	%	ISO 527
Tensile Modulus, 1 mm/min	2400	MPa	ISO 527
Flexural Stress, yield, 2 mm/min	80	MPa	ISO 178
Flexural Modulus, 2 mm/min	2400	MPa	ISO 178
IMPACT			
Izod Impact, notched, 23°C	170	J/m	ASTM D 256
Izod Impact, notched, -30°C	64	J/m	ASTM D 256
Instrumented Impact Total Energy, 23°C	39	J	ASTM D 3763
Instrumented Impact Total Energy, -30°C	33	J	ASTM D 3763
Izod Impact, notched 80*10*4 +23°C	21	kJ/m ²	ISO 180/1A
Izod Impact, notched 80*10*4 -30°C	6	kJ/m ²	ISO 180/1A
Charpy 23°C, V-notch Edgew 80*10*4 sp=62mm	37	kJ/m ²	ISO 179/1eA
THERMAL			
HDT, 0.45 MPa, 3.2 mm, unannealed	102	°C	ASTM D 648
HDT, 1.82 MPa, 6.4 mm, unannealed	90	°C	ASTM D 648
CTE, -20°C to 150°C, flow	7.2E-05	1/°C	ASTM E 831
CTE, -20°C to 150°C, xflow	7.2E-05	1/°C	ASTM E 831
Thermal Conductivity	0.25	W/m-°C	ASTM C177
Vicat Softening Temp, Rate B/50	109	°C	ISO 306
HDT/Bf, 0.45 MPa Flatw 80*10*4 sp=64mm	107	°C	ISO 75/Bf
HDT/Af, 1.8 MPa Flatw 80*10*4 sp=64mm	93	°C	ISO 75/Af
Relative Temp Index, Elec	50	°C	UL 746B
Relative Temp Index, Mech w/impact	50	°C	UL 746B
Relative Temp Index, Mech w/o impact	50	°C	UL 746B
PHYSICAL			
Specific Gravity	1.14	-	ASTM D 792

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
Water Absorption, 24 hours	0.24	%	ASTM D 570
Mold Shrinkage, flow, 3.2 mm	0.5 – 0.7	%	SABIC method
Mold Shrinkage, xflow, 3.2 mm	0.5 – 0.7	%	SABIC method
Melt Flow Rate, 220°C/10.0 kgf	6.7	g/10 min	ASTM D 1238
Melt Flow Rate, 260°C/5.0 kgf	18	g/10 min	ASTM D 1238
Melt Flow Rate, 280°C/3.8 kgf	31	g/10 min	ASTM D 1238
OPTICAL			
Gloss, untextured, 60 degrees	90	-	ASTM D 523
FLAME CHARACTERISTICS			
UL Yellow Card Link	E121562-220666	-	-
UL Recognized, 94HB Flame Class Rating	1.47	mm	UL 94
INJECTION MOLDING			
Drying Temperature	90 – 100	°C	
Drying Time	3 – 4	hrs	
Drying Time (Cumulative)	8	hrs	
Maximum Moisture Content	0.04	%	
Melt Temperature	255 – 270	°C	
Nozzle Temperature	240 – 255	°C	
Front - Zone 3 Temperature	245 – 260	°C	
Middle - Zone 2 Temperature	240 – 255	°C	
Rear - Zone 1 Temperature	230 – 250	°C	
Mold Temperature	55 – 70	°C	
Back Pressure	0.3 – 1	MPa	
Screw Speed	30 – 80	rpm	
Shot to Cylinder Size	40 – 80	%	
Vent Depth	0.038 – 0.076	mm	
SHEET EXTRUSION			
Drying Temperature	90 – 100	°C	
Drying Time	3 – 4	hrs	
Drying Time (Cumulative)	8	hrs	
Minimum Moisture Content	0.04	%	
Melt Temperature	255 – 270	°C	
Barrel - Zone 1 Temperature	220 – 230	°C	
Barrel - Zone 2 Temperature	230 – 245	°C	
Barrel - Zone 3 Temperature	245 – 255	°C	
Barrel - Zone 4 Temperature	255 – 265	°C	
Adapter Temperature	255 – 265	°C	
Die Temperature	255 – 265	°C	
Roll Stack Temp - Top	100 – 120	°C	
Roll Stack Temp - Middle	95 – 110	°C	
Roll Stack Temp - Bottom	75 – 90	°C	



DISCLAIMER

Any sale by SABIC, its subsidiaries and affiliates (each a "seller"), is made exclusively under seller's standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NONINFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer's particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.