

#### **RMW** Raychem

## Medium wall, polyolefin heat-shrinkable tubing

Medium wall, general purpose RMW tubing is specifically designed for use in a broad range of low-voltage applications. RMW is tough and flexible, making it particularly suitable for the insulation and protection of cable joints in low voltage electrical systems as well as for cable repair. Uncoated RMW provides insulation and strain relief. Adhesive-lined RMW also provides an environmental seal.

RMW withstands mechanical abuse for increased product reliability. It is made from tough, abrasion-resistant,

crosslinked polyolefin which is resistant to impact and abrasion.

Adhesive-lined RMW provides a complete moisture-proof seal, preventing corrosion of underlying components. It is resistant to chemicals and moisture. The thermoplastic adhesive in RMW will adhere to most common polymeric- and elastomericinsulated cables as well as to metals such as lead and aluminum.

Installation is fast and easy and requires no special skills. When heated, RMW tubing shrinks quickly and conforms tightly to the substrate. While adhesive-lined RMW tubing is shrinking, the internal adhesive coating melts and flows to environmentally seal the splice, cable jacket or termination on which it is being installed.

RMW is the ideal choice for applications where maximum reliability and product performance, and simplified installation are required. Because RMW is heatshrinkable, a minimum number of sizes are needed to cover a wide range of diameters.


Full recovery temperature:	125°C	
Continuous operating temperature:	−55°C to 110°C	

Specifications
Туре

Raychem RMW **RMW SCD** 

### Dimensions (millimeters/inches)





	Inside diameter				Recovered wall thickness**				Inside diameter			Recovered wall thickness**					
	D (n	nin.)	d (m	nax.)	W		W1			D (m	in.)	d (m	ах.)	W		W1	
	Expa	anded	Rec	overed	(nom.)	)	(nom.)			Expa	nded	Rec	overed	(nom.)	)	(nom.)	
Size	as s	upplied	afte	r heating	Jacke	t wall	Adhesi	ve wall	Size	as sı	upplied	afte	r heating	Jacke	t wall	Adhesi	ve wall
10/3	10	0.394	3	0.118	1.0	0.039	0.25	0.010	85/25	85	3.346	25	0.984	2.8	0.110	0.40	0.016
16/5	16	0.630	5	0.197	1.4	0.055	0.30	0.012	95/29	95	3.740	29	1.142	3.1	0.122	0.45	0.018
25/8	25	0.984	8	0.315	2.0	0.079	0.35	0.014	115/34	115	4.527	34	1.339	3.1	0.122	0.45	0.018
35/12	35	1.693	12	0.472	2.0	0.079	0.35	0.014	140/42	140	5.512	42	1.654	3.1	0.122	0.45	0.018
50/16	50	1.968	16	0.630	2.0	0.079	0.35	0.014	160/50	160	6.299	50	1.968	3.2	0.126	0.50	0.020
63/19	63	2.480	19	0.748	2.4	0.095	0.40	0.016	180/60	180	7.087	60	2.362	3.2	0.126	0.50	0.020
75/22	75	2 953	22	0.866	27	0.106	0.40	0.016									

<sup>\*\*</sup>Wall thickness will be less if tubing recovery is restricted during shrinkage.

### Ordering information

Color	Black
Size selection	Always order the largest size that will shrink snugly over the component being covered.
Standard packaging	1200MM lengths
Marking	Tubing will be marked with the product name, size and batch number.
Ordering description	Specify product name, size, cut length, coating option and color; for example, RMW-25/8-1200/ADH-0 or RMW-75/22-
	1200/U-0 (ADH = Adhesive-lined, U=Uncoated, 0=Black).

<sup>\*</sup>When ordering, always specify latest issue.

8/02

© 2002 Tyco Electronics Corporation Printed in USA 1654077

	Property	Unit	Requirement	Method of test	
Material	Dimensions	mm (inches)	See reverse	ASTM D 412	
	Longitudinal change	percent	+5, –15	ASTM D 792	
	Tensile strength	psi <i>(MPa)</i>	ASTM D 412		
	Ultimate elongation	percent	350 minimum	ASTM D 792	
	Specific gravity		1.2 maximum	ASTM D 792	
	Hardness	Shore D	50 to 70	ASTM D 2240	
	Low temperature flexibility (4 hours at -55°C/-67°F)		No cracking	ASTM D 2671	
	Heat resistance (168 hours at 150°C/302°F) Followed by test for:		250 minimum	ACTNA D 2774	
	Ultimate elongation	percent	350 minimum	ASTM D 2671	
Electrical	Dielectric strength	volts/mil (kVmm)	500 <i>(200)</i> minimum	ASTM D 149	
	Volume resistivity	ohm-cm	1 x 10 <sup>12</sup> minimum	ASTM D 257	
Chemical	Corrosive effect (16 hours at 150°C/302°F)		Noncorrosive	ASTM D 2671 Procedure A	
	Fungus resistance		Rating of 1 or less	ASTM G 21	
	Water absorption (24 hours at 23 °C/73°F)	percent	percent 0.1 maximum		
	Fluid resistance (168 hours at 23°C/73°F) in: VDE 0370 oil Followed by tests for:			ASTM D 2671	
	Tensile strength	psi	85% minimum of original	ASTM D 2671	
	Ultimate elongation	percent	85% minimum of original	ASTM D 2671	

### Typical performance values

	Property	Unit	Performance	Method of Test
Adhesive Properties	Softening point	°C	90 ± 10	ASTM E 28
	Peel Strength			ASTM D 1000
	Copper		10 lbs./in. width	
	Polyethylene		10 lbs./in. width	
	Adhesive Shear	psi	150 minimum	ASTM D 1002
	Aluminum to aluminum			
	Water absorption	percent	0.5 maximum	ASTM D 570
	Corrosive effect	·	Noncorrosive	ASTM D 2671
	(16 hours at 121°C/250°F)			Procedure A

Raychem is a trademark of Tyco Electronics Corporation.

#### Users should independently evaluate the suitability of the product for their application.

Tyco Electronics Corporation 300 Constitution Drive Menlo Park, CA 94025-1164 USA

Tel: (800) 926-2425 (US & Canada) Tel: +1 (650) 361-3860 (All other countries) Faraday Road Dorcan, Swindon, SN3 5HH United Kingdom Tel: +44 1793 528171 3816 Noborito, Tama-ku Kawasaki, Kanagawa 214-8533 Japan

26 Ang Mo Kio, Industrial Park 2 Singapore 569507 Tel: +65 4866 151

Asia Pacific Headquarters

# **Mouser Electronics**

**Authorized Distributor** 

Click to View Pricing, Inventory, Delivery & Lifecycle Information:

# TE Connectivity:

RMW16/51200/ADH0 RMW-10/3-1200/ADH-0 RMW-16/5-1200/ADH-0