

# Technical Datasheet

## Elecolit® 3012



### Product Description

Panacol Elecolit® adhesives are solvent free single or two-component adhesives. They are mostly based on epoxy resin and can be cured at room temperature or by exposure of heat. Elecolit® adhesives are electrically and / or thermally conductive adhesives which are designed for potting, bonding or contacting of conductors.

Elecolit® 3012 is a silver-filled, solvent-free, pasty conductive adhesive. Elecolit® 3012 has a good gap-filling capacity and can be processed with dispenser or screen-printing. Elecolit® 3012 should have reached room temperature before opening the can to prevent condensation.

### Curing Properties

The product is a one-component adhesive and cures under exposure to heat. Possible curing temperatures are listed in the table below.

Thermal curing	min
Time at 100°C	120
Time at 120°C	18
Time at 150°C	4

The curing times given are guidelines. They refer to rheological measurements according to PE-Norm 067 . The heating up of the joining members are not taken into account.

The final strength of the adhesive is reached at the earliest after 24 h.

### Technical Data

Resin	epoxy
Appearance	grey
Filler	silver
Filler – weight [%]	75
Particle size D95 [µm]	20

### Uncured material

Viscosity [mPas]	paste-like
Density [g/cm³]	2,0
PE-Norm 004	
Flash point [°C]	>100
PE-Norm 050	

### Cured material

Hardness shore D	82
PE-Norm 006	
Temperature resistance [°C]	-40 - 200
Water absorption [mass %]	<0,5
PE-Norm 016	

# Technical Datasheet

## Elecolit® 3012



Glass transition temperature DSC [°C] <i>PE-Norm 009</i>	102
Coefficient of thermal expansion [ppm/K] below Tg <i>PE-Norm 017</i>	67
Thermal conductivity [W/m*K] <i>PE-Norm 062</i>	2
Volume resistivity [Ohm*cm] <i>PE-Norm 040</i>	1,E-02

### Transport/Storage/Shelf Life

Trading unit	Transport	Storage	Shelf-life*
Cartridge	0°C - 10°C	-20°C	at delivery min. 3 months max. 6 months
Other packages			

**\*Store in original, unopened containers!**

### Instructions for Use

#### Surface preparation

The surfaces to be bonded should be free of dust, oil, grease or other dirt in order to obtain an optimal and reproducible bond.

For cleaning we recommend the cleaner IP® Panacol. Substrates with low surface energy (e.g. polyethylene, polypropylene) must be pretreated in order to achieve sufficient adhesion.

#### Application

Our products are supplied ready to use. Depending on packaging they can be applied by hand directly from the container or semi or fully automatically. With automated application from the cartridge the adhesive is conveyed by a compressed air-operated displacement plunger via a valve in the needle. When metering low viscosity materials from bottles the adhesive is transported by a diaphragm valve. If help is required, please contact our application engineering department.

Adhesive and substrate may not be cold and must be warmed up to room temperature prior to processing.

For safety information refer to our safety data sheet.

# Technical Datasheet

## Elecolit® 3012



### Disclaimer

The product is free of heavy metals, PFOS and Phthalates and is conform to the EU-Directive 2017/2102/EU "RoHS III".

**THE VALUES NOTED IN THIS TECHNICAL DATA SHEET ARE TYPICAL PROPERTIES AND ARE NOT MEANT TO BE USED AS PRODUCT SPECIFICATIONS.**

The information contained in this data sheet is believed to be accurate and is provided for information only. Panacol makes no representation or warranties of any kind concerning this information. It is the user's responsibility to determine the suitability of this product for any intended use. Panacol does not assume responsibility for test or performance results obtained by the user. The user assumes all risk and liability connected with the use of this product.

The user should adopt such precautions and use guidelines as may be advisable for the protection of property and persons against any hazards that may be involved in this product's handling or use. Panacol specifically disclaims any liability for consequential or incidental damages of any kind arising from the handling or use of this product.

The information contained in this Technical Data Sheet offers no assurance that the product use, application, or process will not infringe on existing patents or licenses of others. Nothing in this Technical Data Sheet transfers or grants license for the use of any patents, trade secrets, intellectual property, or confidential information that is the property of Panacol.

Except as otherwise noted, all trademarks in this document (identified as ®) are the property of Panacol.

### Contact

**Panacol-Elosol GmbH**  
Daimlerstr. 8  
61449 Steinbach  
Germany  
Phone: +49 6171 6202-0  
Mail: info@panacol.de  
[www.panacol.com](http://www.panacol.com)

**Panacol-USA, Inc.**  
142 Industrial Lane  
Torrington CT 06790  
USA  
Phone: +1 860-738-7449  
Mail: info@panacol-usa.com  
[www.panacol-usa.com](http://www.panacol-usa.com)

**Panacol-Korea Co., Ltd.**  
#707, Kranz Techno, 388 Dunchon-daero  
Junwon-gu, Seongnam  
Gyeonggi-do, 13403 KOREA  
Phone: +82 31 749 1701  
Mail: info@panacol-korea.com  
[www.panacol-korea.com](http://www.panacol-korea.com)

**Eleco Panacol – EFD**  
125, av Louis Roche  
Z.A. des Basses Noëls  
92238 Gennevilliers Cdx FRANCE  
Tél.: +33 (0)1 47 92 41 80  
Mail: eleco@eleco-panacol.fr  
[www.eleco-panacol.fr](http://www.eleco-panacol.fr)