

Heat Shrink Tubing

pro-POWER



Description:

The PHS series is a flexible, adhesive-lined, flame retardant, thin wall polyolefin with an integral internal layer of special thermoplastic adhesive that bonds with a wide variety of rubber, plastics and metals, forming a permanent, non-drying, flexible and water proof barrier.

Features:

Shrink Ratio : 3 : 1
Shrink Temp : 121°C (259°F)
Operating Temp : -55°C to +110°C (-67°F to +230°F)

Dimensions				Standard Packages (Colour: Black)					
Size	Expanded I.D.(Min.)	Recovered I.D.(Max.)	Recovered Nominal Wall Thickness	4 Foot Lengths (+1", -0")			6 Inch Lengths (± .125")		
				Part Number	Pcs	Total Footage	Part Number	Pcs	Total Footage
1/8"	0.125"	0.04"	0.04"	NA			PHS-008-6028-BLK	28	14ft
3/16"	0.187"	0.062"	0.04"	PHS-012-4025-BLK	25	100ft	PHS-012-6024-BLK	24	12ft
1/4"	0.25"	0.08"	0.04"	PHS-016-4025-BLK	25	100ft	PHS-016-6020-BLK	20	10ft
3/8"	0.375"	0.12"	0.055"	PHS-024-4025-BLK	25	100ft	PHS-024-6016-BLK	16	8ft
1/2"	0.5"	0.16"	0.07"	PHS-032-4005-BLK	5	20ft	PHS-032-6014-BLK	14	7ft
3/4"	0.75"	0.25"	0.085"	PHS-048-4005-BLK	5	20ft	PHS-048-6012-BLK	12	6ft
1"	1"	0.32"	0.1"	PHS-064-4005-BLK	5	20ft	NA		
1 1/2"	1.5"	0.51"	0.1"	PHS-096-4005-BLK	5	20ft	PHS-096-6005-BLK	5	2.5ft

Typical Properties

Dimensions : Inches (mm)

Physical

Tensile Strength : 2,100 PSI
Ultimate Elongation : 450%
Longitudinal Change : +1% to -15%
Secant Modulus (2%) : 17,000 PSI
*Heat Aging Elongation : 175%
(168 hrs @ 175°C)
*Heat Shock : No dripping, cracking or flowing
(4 hrs @ 225°C)
*Low Temp Flexibility : No cracking
(4 hrs @ -55°C)
**Flexibility : 3
*Outer wall only
**Flexibility: The material are rated on a scale of 1 to 10. (1 = most flexible and 10 = most rigid)

www.element14.com
www.farnell.com
www.newark.com
www.cpc.co.uk

pro-POWER

Electrical

Dielectric Strength : 700V / mil
Volume Resistivity : 10^{14} ohm-cm

Chemical

Corrosive Effect : Non-corrosive
Water Absorption : 0.3%
Fungus Resistance : Non-nutrient
Fluid Resistance : Excellent
Applicable Specifications : MIL-DTL-23053/4 Class 3

Adhesive

Peel Strength, pli
Polyethylene : 30
PVC : 10
Lead : 15
Aluminum : 40
Corrosive Effect : Non-corrosive

The technical information provided consists of typical product data and should not be used for specification purposes. Unless otherwise noted, all tests are performed at room temperature.

Part Number Table

Description	Part Number
Heat Shrink Tubing	PHS-012-4025-BLK
	PHS-016-4025-BLK
	PHS-024-4025-BLK
	PHS-032-4005-BLK
	PHS-048-4005-BLK
	PHS-064-4005-BLK
	PHS-096-4005-BLK
	PHS-008-6028-BLK
	PHS-012-6024-BLK
	PHS-016-6020-BLK
	PHS-024-6016-BLK
	PHS-032-6014-BLK
	PHS-048-6012-BLK
	PHS-096-6005-BLK

Important Notice : This data sheet and its contents (the "Information") belong to the members of the Premier Farnell group of companies (the "Group") or are licensed to it. No licence is granted for the use of it other than for information purposes in connection with the products to which it relates. No licence of any intellectual property rights is granted. The Information is subject to change without notice and replaces all data sheets previously supplied. The Information supplied is believed to be accurate but the Group assumes no responsibility for its accuracy or completeness, any error in or omission from it or for any use made of it. Users of this data sheet should check for themselves the Information and the suitability of the products for their purpose and not make any assumptions based on information included or omitted. Liability for loss or damage resulting from any reliance on the Information or use of it (including liability resulting from negligence or where the Group was aware of the possibility of such loss or damage arising) is excluded. This will not operate to limit or restrict the Group's liability for death or personal injury resulting from its negligence. pro-POWER is the registered trademark of the Group. © Premier Farnell plc 2012.