

TECHNICAL DATA SHEET

www.tycoident.com

Document number: TTDS-075
Issue: 3
Date: June 2003

HM high tack metalized polyester

MATERIAL DESCRIPTION:	Tyco "HM" is a thermal transfer printable metalized polyester film with a high tack permanent acrylic adhesive.	
USE:	Ideal for rating plates and other labels requiring a "metal" look. The 'high-tack' adhesive is designed to bond to the most demanding surfaces including textured and contoured surfaces. For guaranteed print performance and durability, use with Tyco's RHD series ribbon.	
PRINT METHOD/RIBBON:	Preferred Printer/Ribbon combination: Thermal Transfer: T308S-PRINTER, Tyco 1330-0607-10 Ribbon Alternative Printer/Ribbon combinations: Thermal Transfer: T312S-PRINTER, Tyco 1330-0607-10 Ribbon Thermal Transfer: T312M-PRINTER, Tyco 1330-0607-10 Ribbon Thermal Transfer: T200 Series, Tyco 1330-3300-101TT Ribbon Thermal Transfer: T400 Series, Tyco 1330-0607-10 Ribbon Dot Matrix: AM6310, Tyco 1892BK04-RIBBON	
SHELF LIFE:	2 years when stored at 21°C (70°F) at 50% R.H.	
ADHESIVE:	'High-tack' permanent acrylic	
COLOR:	Bright silver	
APPROXIMATE TOTAL THICKNESS:	Facestock:	0.051mm (0.0020 in)
	Adhesive:	0.046mm (0.0018 in)
	Liner:	0.038mm (0.0015 in)

Page 1 of 3

Business locations:

☎ France: +33 (0) 476 099696 (Labels)
☎ Germany: + 49 (0) 6074 89080
☎ UK: + 44 (0) 1495 244000 (Labels)
☎ Japan: + 81 (0) 44 900 5102

☎ N America: + 1 401 751 6505 (East Coast)
☎ France: + 33 (0) 134 20 21 22 (Other products)
☎ UK: + 44 (0) 1793 528171 (Other products)
☎ Singapore: + 65 (0) 4866 151

All the above information, including illustrations, is believed to be reliable. Users, however, should independently evaluate the suitability of each product for their application. Tyco Electronics makes no warranties as to the accuracy or completeness of the information and disclaims any liability regarding its use. Tyco Electronics only obligations are those in the Standard Terms and Conditions of Sale for this product and in no case will Tyco Electronics be liable for any incidental, indirect or consequential damages arising from the sale, resale, use or misuse of the product. Tyco Electronics Specifications are subject to change without notice. In addition Tyco Electronics reserves the right to make changes in materials or processing, without notification to the Buyer, which do not affect compliance with any applicable specification.

TECHNICAL DATA SHEET

www.tycoident.com

Document number: TTDS-075
Issue: 3
Date: June 2003

HM high tack metalized polyester

ADHESION:	ASTM-D-3330 (180° peel direction), 10minute dwell at 21°C (70°F): Stainless Steel: typical failure at 96N/100mm (88oz/in) Polycarbonate: typical failure at 98N/100mm (90oz/in) Polypropylene: typical failure at 80N/100mm (73oz/in) HDPE: typical failure at 59N/100mm (54oz/in) Smooth Powder coating: typical failure at 93N/100mm (85oz/in) Finely Textured Powder coating: typical failure at 54N/100mm (49oz/in) Glass: typical failure at 102N/100mm (93oz/in)
SERVICE TEMPERATURE:	-40° C to 150° C (-40° F to 302° F)
MINIMUM APPLICATION TEMPERATURE:	10°C (50°F)
SOLDER IMMERSION:	After 10-second immersion at 250°C (480°F) in molten solder: slight yellowing, print remains legible.
FLAMMABILITY:	UL94 rating 94VTM-2, slow to self extinguish
UV TRANSMISSIBILITY:	< 0.01%
ABRASION RESISTANCE:	Print remains legible for 100 revolutions of CS-10 wheels with 500 gram load (Taber-Abraser Model 5130). Print remains legible after repeated rub testing as per AS-81531
CHEMICAL SOAK RESISTANCE:	Excellent resistance with minimal edge penetration: Samples soaked in fluids for four hours at room temperature, unless otherwise stated. Samples applied to stainless steel panels 24 hours prior to immersion and evaluated one hour after removal from the fluids. Adhesion measured at 180° peel angle per ASTM D3330. Typical Results:

<u>Chemical</u>	<u>Adhesion</u>	<u>Effect</u>	<u>Edge Penetration</u>
Isopropyl alcohol	96N/100mm	No change	0.6mm
Detergent	101N/100mm	No change	1.3mm
Engine Oil	112N/100mm	No change	0.6mm
Water (48 hours)	73N/100mm	No change	0.1mm

Page 2 of 3

Business locations:

☎ France: +33 (0) 476 099696 (Labels)
☎ Germany: + 49 (0) 6074 89080
☎ UK: + 44 (0) 1495 244000 (Labels)
☎ Japan: + 81 (0) 44 900 5102

☎ N America: + 1 401 751 6505 (East Coast)
☎ France: + 33 (0) 134 20 21 22 (Other products)
☎ UK: + 44 (0) 1793 528171 (Other products)
☎ Singapore: + 65 (0) 4866 151

All the above information, including illustrations, is believed to be reliable. Users, however, should independently evaluate the suitability of each product for their application. Tyco Electronics makes no warranties as to the accuracy or completeness of the information and disclaims any liability regarding its use. Tyco Electronics only obligations are those in the Standard Terms and Conditions of Sale for this product and in no case will Tyco Electronics be liable for any incidental, indirect or consequential damages arising from the sale, resale, use or misuse of the product. Tyco Electronics Specifications are subject to change without notice. In addition Tyco Electronics reserves the right to make changes in materials or processing, without notification to the Buyer, which do not affect compliance with any applicable specification.

TECHNICAL DATA SHEET

www.tycoident.com

Document number: TTDS-075
Issue: 3
Date: June 2003

HM high tack metalized polyester

Toluene	55N/100mm	No change	5.2mm
Acetone	65N/100mm	No change	4.9mm
Brake Fluid	107N/100mm	No change	0.1mm
Gasoline	61N/100mm	No change	4.6mm
Diesel Fuel	102N/100mm	No change	0.7mm
Hydraulic Fluid	105N/100mm	No change	0.0mm

PRINT PERFORMANCE:

Good resistance to fluids- see below Samples printed using Tyco recommended ribbons. All tests conducted at room temperature unless otherwise stated

SOLVENT	TEST	EFFECT
IPA	7 day immersion	No visual effect
Water	7 day immersion	No visual effect
Engine Oil at 250°F (121°C)	48 hour soak	No visual effect
Engine Coolant at 200°F (93°C)	4 hour soak	No visual effect

Page 3 of 3

Business locations:

☎ France: +33 (0) 476 099696 (Labels)
☎ Germany: + 49 (0) 6074 89080
☎ UK: + 44 (0) 1495 244000 (Labels)
☎ Japan: + 81 (0) 44 900 5102

☎ N America: + 1 401 751 6505 (East Coast)
☎ France: + 33 (0) 134 20 21 22 (Other products)
☎ UK: + 44 (0) 1793 528171 (Other products)
☎ Singapore: + 65 (0) 4866 151

All the above information, including illustrations, is believed to be reliable. Users, however, should independently evaluate the suitability of each product for their application. Tyco Electronics makes no warranties as to the accuracy or completeness of the information and disclaims any liability regarding its use. Tyco Electronics only obligations are those in the Standard Terms and Conditions of Sale for this product and in no case will Tyco Electronics be liable for any incidental, indirect or consequential damages arising from the sale, resale, use or misuse of the product. Tyco Electronics Specifications are subject to change without notice. In addition Tyco Electronics reserves the right to make changes in materials or processing, without notification to the Buyer, which do not affect compliance with any applicable specification.