

# Primary lithium battery

## LS 17500

3.6 V Primary lithium-thionyl chloride (Li-SOCl<sub>2</sub>)  
High energy density  
A-size bobbin cell



### Benefits

- High voltage response, stable during most of the lifetime of the application
- Wide operating temperature range (-60/+85°C)
- Low self-discharge rate (less than 1 % after 1 year of storage at +20°C)
- Easy integration into compact systems
- Superior resistance to atmospheric corrosion

### Key features

- Stainless steel container and end caps (low magnetic signature)
- Hermetic glass-to-metal sealing
- Non-flammable electrolyte
- Underwriters Laboratories (UL) Component Recognition
- Compliant with IEC 60086-4 safety standard and IEC 60079-11 intrinsic safety standard (class T3 assignment)
- Non-restricted for transport/ Non-assigned to Class 9 according to the UN Recommendations on the transport of dangerous goods – Model Regulations
- Manufactured in France

### Main applications

- Utility metering
- Automatic meter reading
- Alarms and security devices
- Tollgate systems
- Identification tags
- Tracking systems
- Automotive electronics
- Professional electronics

### Cell size reference

A

### Electrical characteristics

(typical values relative to cells stored for one year or less at +30°C max.)

Nominal capacity 3.6 Ah  
(at 3 mA +20°C 2.0 V cut-off. The capacity restored by the cell varies according to current drain, temperature and cut-off)

Open circuit voltage (at +20°C) 3.67 V

Nominal voltage (at 0.3 mA +20°C) 3.6 V

Nominal energy 12.96 Wh

Pulse capability: Typically up to 250 mA  
(250 mA/0.1 second pulses, drained every 2 mn at +20°C from undischarged cells with 10 µA base current, yield voltage readings above 3.0 V. The readings may vary according to the pulse characteristics, the temperature, and the cell's previous history. Fitting the cell with a capacitor may be recommended in severe conditions. Consult Saft)

Maximum recommended continuous current 100 mA  
(Higher currents are possible. Consult Saft)

Storage (recommended) +30°C (+86°F) max  
(for more severe conditions, consult Saft)

Operating temperature range -60°C/+85°C  
(-76°F/+185°F)  
(Operation above ambient T may lead to reduced capacity and lower voltage readings at the beginning of pulses. Consult Saft)

### Physical characteristics

Diameter (max) 17.13 mm (0.67 in)

Height (max) 50.9 mm (2.00 in)

Typical weight 21.9 g (0.8 oz)

Li metal content approx. 0.9 g


Available termination suffix

|                           |                     |
|---------------------------|---------------------|
| CN, CNR                   | radial tabs         |
| 2 PF, 3 PF, 3 PF RP, 4 PF | radial pins         |
| CNA (AX)                  | axial leads         |
| FL                        | flying leads...etc. |



**saft**

# LS 17500



Dimensions in mm.


## Storage

- The storage area should be clean, cool (*preferably not exceeding +30°C*), dry and ventilated.


## Warning

- Fire, explosion and burn hazard.
- Do not recharge, short circuit, crush, disassemble, heat above 100°C (212°F), incinerate, or expose contents to water.
- Do not solder directly to the cell (*use tabbed cell versions instead*).


Voltage plateau versus Current and Temperature (at mid-discharge)



Typical discharge profiles at +20°C



Restored Capacity versus Current and Temperature (2.0 V cut-off)



## Saft

### Specialty Battery Group

12, rue Sadi Carnot  
93170 Bagnolet - France  
Tel.: +33 (0)1 49 93 19 18  
Fax: +33 (0)1 49 93 19 69

[www.saftbatteries.com](http://www.saftbatteries.com)

Doc. N° 31029-2-0710

Information in this document is subject to change without notice and becomes contractual only after written confirmation by Saft.

For more details on primary lithium technologies please refer to Primary Lithium Batteries Selector Guide Doc N° 31048-2.

Published by the Communications Department.

Photo credit: Saft

Société anonyme au capital de 31 944 000 €  
RCS Bobigny B 383 703 873

Produced by Arthur Associates Limited.



**SAFT**