

Tgard[™] 500 Thermally Conductive Insulators



THICKER THERMAL INSULATOR PAD PREVENTS ELECTRICAL SHORTS IN AUTOMOTIVE ELECTRONICS APPLICATIONS

Tgard™ 500 is a medium thermal performance insulator pad consisting of a ceramic filled high temperature silcone rubber coated on electrical grade fiberglass.

Tgard 500 is designed for applications that require tadditional thickenss to prevent electrical shrots form stamped aluminumheatskinks used in switching mode power supplies (SMPS) and debris from aluminum castings used in automotive motor controls.

FEATURES AND BENEFITS

- High breakdown voltage of > 6,000 volts AC
- Thermal resistance of 0.48° C-in2/watt at 50 psi
- Thermal resistance of 0.28º C-in2/watt at 400 psi
- Thick enough to encapsulate burrs of stamped heatskinks

APPLICATIONS

- · Automotive motor controls
- Switching mode power supplies
 - stamped aluminum heatsinks

Americas: +1.847 839.6907 IAS-AmericasEastSales@lairdtech.com

Europe: +44.1628.858941
IAS-EUSales@lairdtech.com
Asia: ++86.21.5855.0827.127
IAS-AsiaSales@lairdtech.com
CLV-customerservice@lairdtech.com
www.lairdtech.com/thermal

Thermally Conductive Insulators

PROPERTIES	TEST M	ETHOD	METRIC VALUES I			MPERIAL VALUES		
ELECTRICAL PROPERTIES								
Dielectric with standard voltage 50mm probe for 30 sec	e ASTM	ASTM D149		4,500 volts AC		4,500 volts AC		
Dielectric breakdown voltage 50mm probe	ASTM	ASTM D149		Avg >6,000 volts AC			Avg >6,000 volts AC	
Volume resistivity	ASTN	D257	10 ¹² ohm-cm			10 ¹² ohr	10 ¹² ohm-in	
Dielectric constant @1Mhz	ASTN	D257	3.3			3.3		
Electrical RTI temperature ratin	g UL7	46D	5D 150ºC			302ºF		
MECHANICAL PROPERTIES								
Thickness			0.23 mm			0.009 in		
Hardness	ASTM	ASTM D2240		80 Shore A		80 Shore A		
Tensile strength	ASTM	ASTM D412		11.7 Mpa		1.7 Kpsi		
Elongation @ 45º to warp/fill	ASTM	ASTM D412		20%			20%	
Elongation along width or lengt	length ASTM D412		5%			5%		
Operating temperature range				-60º to 180ºC			-76º to 356ºF	
Color			Brown Brown			n		
UL flammability rating	UL	94	V-0		V-0			
PRESSURE	UNITS	10 (69)	25 (172)	50 (345)	100 (689)	200 (1379)	400 (2758)	
TOTAL THERMAL RESISTANCE								
Modified ASTM D5470	ºC-in²/watt	0.81	0.70	0.48	0.33	0.30	0.28	
Modified ASTM D5470	ºC-cm²/watt	5.16	4.52	3.21	2.13	1.94	1.80	
T0-220	ºC/watt	1.29	1.01	0.95	0.79	0.77	0.76	

Standard thickness: 9 mils (0.229 mm)

Configurations available: • Sheet form, roll form and die-cut parts

• Single-side, pressure-sensitive adhesive on request

Standard options: • Without adhesive (A0): 12 x 18" sheets, 12" x 65M,

12" x 30M roll or custom configuration

• With adhesive (A1): 11.75 x 18" sheets, 11.75" x 30M roll

or custom configuration

Data for design engineer guidance only. Observed performance varies in application. Engineers are reminded to test the material in application.

Mouser Electronics

Authorized Distributor

Click to View Pricing, Inventory, Delivery & Lifecycle Information:

Laird Technologies:

A15397-03	A15397-04	A15440003	A15036002	A15433002	A15037001	A15428002	A15436002	A15432002
A15435002	A15431002	A15440102	A15441102	A15434102	A15037002	A15038-002	A15437002	A15431102
A15038102	A15427102	A15440002	A15434002	A15436102	A15435102	A15432102	A15037102	A15441002
A15430102	A15427002	A15437102	A15428102	A15036102	A15430002	A15433102		