

1. GENERAL DESCRIPTION

Workshop spatter release based on bio degradable oil (CEC-I-33-T-82). CRC Easy Weld provides a quick, easy way to prevent adherence of spatter to metal surfaces during welding and eliminates the need for chiselling, grinding or wire brushing after welding. It prevents the obstruction of automatic and semi-automatic welding equipment.

2. FEATURES

- Non-silicone heat resistant barrier.
- Long-term anti-adherent effect.
- Easy removal of welding spatter by brushing.
- Economical use, due to its thin film performance.
- Extended nozzle life.
- Increased stability of the arc, ensuring free gas flow.
- Contains effective corrosion inhibitors to protect treated surfaces and equipment.
- Aerosols are equipped with the 360°C (upside-down) spray valve for added convenience.
- Pressurised with a hydrocarbon propellant.


3. APPLICATIONS

- Workpieces and parts
- Jigs
- Fixtures
- Nozzles and shrouds
- Torches
- Automatic and semi-automatic welding
- Welding robots

4. DIRECTIONS

- Apply a thin, even film on the surfaces to be welded.
- Spray into the welding nozzle before starting and re-apply as required.
- Protect aerosol can against spatters, extremely flammable formulation.
- Spatter can be wiped off with a cloth or by tapping the nozzle on the side of the bench.
- Residual product film may be removed by CRC Industrial Degreaser or CRC Fast Dry Degreaser. In case the post treatment is Hot Dip Galvanizing, follow the cleaning instructions from the galvanizing company or the galvanizing federations (info via International Zinc Association: www.iza.com)
- Provide good ventilation during welding.
- A safety data sheet (MSDS) according to EU directive 91/155/EEC and amendments is available for all CRC products.





5. TYPICAL PRODUCT DATA (without propellant)

Appearance	: light amber liquid
Distillation range of solvent	: 35-65°C
Flash point	: < 0°C
Freezing point	: < -30°C
Vapour density (vs. air = 1)	: > 1
Dry film properties	
Flash point	: 250°C
Specific gravity (@ 20°C)	: 0,92
Typical film thickness	: 2-5 µm

6. PACKAGING

aerosol : 12 x 400 ml

7. SPECIAL REMARK

The formula is extremely flammable. Keep the aerosol protected from any source of ignition.

All statements in this publication are based on service experience and/or laboratory testing. Because of the wide variety of equipment and conditions and the unpredictable human factors involved, we recommend that our products be tested on-the-job prior to use. All information is given in good faith but without warranty neither expressed nor implied.

This Technical Data Sheet may already have been revised at this moment for reason such as legislation, availability of components and newly acquired experiences. The latest and only valid version of this Technical Data Sheet will be sent to you upon simple request or can be found on our website: www.crcind.com.

We recommend you to register on this website for this product so you will be able to receive any future updated version automatically.

Version : 10956 03 0899 05
Date : 15 November 2006



Manufactured by :
CRC Industries Europe BVBA
Touwslagerstraat 1 – 9240 Zele – Belgium
Tel (32) (0) 52/45.60.11 Fax (32) (0) 52/45.00.34
www.crcind.com

