

Desiccant

Tyvek Plastic or Kraft Paper Pouch

This efficient desiccant begins its work by absorbing air borne moisture left inside the bag when you've finished vacuum packaging. Then it captures moisture that manages to pass through the bag material. Secured in a strong envelope of either clean room compatible, sulphur-free Tyvek or economical Kraft Paper, SCC desiccant helps keep your devices dry, even through unexpected shipping delays or longer than anticipated storage time.

Standards

MIL-D-3464, EIA 583, IPC/JEDEC J-STD-033

Specifications

Pouch:	Kraft paper or Tyvek plastic
Print:	Blue ink
Unit sizes:	1/6, 1/3, 1/2, 1, 2, 4, 8, 16
Media:	montmorillonte clay
Form:	Free flowing even when fully saturated.
Packaging:	Air tight pails or drums



Tyvek Plastic



Kraft Paper

Sizes

Bag Size	Bags per Container	Tyvek Bags P/N	Kraft Bags P/N	Container Weight	Width	Pouch Size	
						Length	Thickness
1/6 Unit	1200	1/6TYDES1200	1/6KDES1200	24	3	3	1/8
1/3 Unit	700	1/3TYDES700	1/3KDES700	25	3	3-1/4	3/16
1/2 Unit	550	1/2TYDES550	1/2KDES550	27	3	3-1/2	1/4
1 Unit	300	1TYDES300	1KDES300	29	5	3-1/2	1/4
1 Unit	1300	1TYDES1300	1KDES1300	114	5	3-1/2	1/4
2 Unit	150	2TYDES150	2KDES150	29	5	4-3/4	3/8
2 Unit	800	2TYDES800	2KDES800	136	5	4-3/4	3/8
4 Unit	500	4TYDES500	4KDES500	163	5	6	1/2
8 Unit	300	8TYDES300	8KDES300	192	5	8	1-1/8
16 Unit	150	16TYDES150	16KDES150	189	5-3/4	10	1-1/2

See SCC Data Sheets for these related items:

Humidity Indicator Cards

Moisture Barrier Bags

Vacuum Sealers

P R O D U C T D A T A S H E E T

Desiccant in Tyvek Plastic or Kraft Paper Pouch

PRODUCT
DESICCANT, TYVEK OR KRAFT POUCH

ITEM NUMBER
SEE ABOVE

DATASHEET
1110-c



STATIC CONTROL COMPONENTS, Inc.
ESD PRODUCTS DIVISION

US and Canada: **866-722-3736**
Fax: 866-722-3735
Intl: 919-774-3808
Fax: 919-774-1287
3010 Lee Avenue Sanford, NC 27330
email: info@staticcontrol.com
www.StaticControl.com

Desiccant

Calculating Desiccant Loading

What is Desiccant?

Desiccant is a drying agent that is used to absorb moisture from the air inside moisture barrier bags. Desiccant absorbs moisture vapor (humidity) from the air left inside the barrier bag after it has been sealed. Any moisture that penetrates the bag will also be absorbed. Desiccant remains dry to the touch even when it is fully saturated with moisture vapor.

How much Desiccant do I need?

Desiccant is sold by the "Unit" or fractional Unit, or in grams. One unit of desiccant will absorb a specific amount of moisture. A unit weighs about 33 grams. There are several standards for calculating the desiccant loading for bags. Each standard is for a specific application, and requires different amounts of desiccant for the same bag size. Once you determine which standard is correct for your dry packing application, apply these formula, or go to www.StaticControl.com and select the Desiccant Calculator.

Why are electronic devices moisture sensitive?

Certain kinds of electronic devices called "Surface Mount Devices" or SMD's are mounted on a circuit card by high temperature soldering. The body of the SMD is made from plastic that absorbs moisture from the air. When the case is heated during soldering, the moisture inside turns to steam, and may break the device as the steam escapes. Keeping SMD's dry before soldering means that the devices will not be damaged.

IPC/JEDEC J-STD-033

Application:

Dry packaging for SMD's.

What You Need Know:

Bag Size, Bag MVTR, Storage Time in Months.

Formula:

Units= $\frac{0.304 \times \text{Months} \times \text{Bag MVTR} \times \text{Bag Area}}{\text{Moisture Capacity}}$

Example:

8" x 10" inch Barrier Bag, with a 0.002 MVTR and a 12 month storage time.

Find Bag Area:

8" x 10" x 2 sides =160 sqin.

Apply Formula:

Units= $\frac{0.304 \times 12 \text{ months} \times 0.002 \text{ MVTR} \times 160 \text{ sqin}}{6.6667 \text{ g/unit}}$

Units = .2 Use 1/6 unit of Desiccant.

EIA 583

Application:

Dry packaging for SMD's. Allows adjustment of environmental conditions.

What You Need Know:

Bag Area, Bag MVTR, Months of Storage, Maximum Interior Humidity (MIH).

Formula:

Units= $\frac{0.231 \times \text{Bag Area} \times \text{Bag MVTR} \times \text{Months}}{\text{Moisture Capacity}}$

Example:

8" x 10" inch Barrier Bag, with a 0.02 MVTR, a 12 month storage time, and a MIH of 20%.

Find Bag Area:

8" x 10" x 2 sides =160 sqin.

Select Moisture Capacity based on MIH:

10% MIH: 3.0 g/unit 20% MIH 4.8 g/unit 30% MIH 5.8 g/unit 40% MIH 6.2 g/unit

Apply Formula:

Units= $\frac{0.231 \times 160 \text{ sqin} \times 0.02 \text{ MVTR} \times 12 \text{ months}}{4.8 \text{ g/unit}}$

Units = 1.8 units Use 2 units of desiccant.

MIL-P-116

Application:

General dry packaging.

What You Need Know:

Bag Size

Formula:

Units = 0.011 x Bag Area in square inches.

Example:

8" x 10" inch Barrier Bag

Find Bag Area:

8" x 10" x 2 sides =160 sqin.

Apply Formula:

Units = 0.011 x 160 sqin = 1.8

Use 2 Units of desiccant.

P R O D U C T D A T A S H E E T

Desiccant in Tyvek Plastic or Kraft Paper Pouch

PRODUCT

DESICCANT, TYVEK OR KRAFT POUCH

ITEM NUMBER

SEE PAGE 1

DATASHEET

1110-c



STATIC CONTROL COMPONENTS, Inc.
ESD PRODUCTS DIVISION

US and Canada: **866-722-3736**
Fax: 866-722-3735
Intl: 919-774-3808
Fax: 919-774-1287
3010 Lee Avenue Sanford, NC 27330
email: info@staticcontrol.com
www.StaticControl.com ©